



NAME: EP-C 30 R

Product Description:

The grade is a hetero-phasic polypropylene copolymer for injection molding the product offers an excellent balance of stiffness.

Application:

Automotive parts, wells, garden furniture, chair shells and stadium seats.

Typical data. (Table)

Property	Unit	Typical Value	Test Method
MFI	Dg/min	7.0	ISO 1133
Density	g/cm ³	0.9	ISO 1183
Flexural Modulus	N/mm ²	1150	ISO 178
Tensile	N/mm ²	26	ISO R527
Elongation	0/%	10	ISO R527
Izod Impact	Kj/m ²	8	ISO 180
Hardness	Point	68	ISO 868
Vicat	°C	151	ISO 306/A
H.D.T	°C	88	ISO 75/B

* Typical Values: not to be construed as specifications

Packing: 25 Kg plastic bag