



NAME: GPPS1340

Product Description:

GPPS1340 is a high molecular weight crystal polystyrene for extrusion and injection molding.

It is particularly useful in the production of sheet with high mechanical properties. GPPS1340 can also be used in dilution with HIPS7240 for extrusion of sheet for thermoforming.

Applications:

Sheet and profile extrusion, packaging, dilution of impact grades for extrusion, injection molding

Typical data: (Table)

PROPERTY	UNIT	METHOD	VALUE
MELT FLOW INDEX(200°C-5KG)	g/10min	ASTM D-1238	4
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA)	<500
VICAT SOFTENING POINT (50 °C/hr	°C	ASTM D-1525	97
ROCKWELL HARDNESS	-	ASTM D-785	SCALE/L70
TENSILE STRESS AT BREAK	MPA	ASTM D-638	51
ELONGATION AT BREAK	%	ASTM D-638	3
TENSILE MODULUS	MPA	ASTM D-638	4410

*All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (standard sales specifications) Density and shrinkage of this grade are approximately around 1.04 kg/lit & (0.4-0.7) % (ASTM D-955) respectively. All test are carried out at 23°C, unless otherwise stated. If the injection molding products quality is affected by moisture, granules of GPPS could be dried at 70°C for 2-4 hours.