



**Linear Low Density Polyethylene LL 6910AA
(Basell Grade: 6910AA) With UV**

Typical applications:

For use in lean and rich blend blown film application such as overwrap, counter bags, shrink film and boil in the bag applications

Technical Data (Table):

Typical properties	Test method (DIN)	Unit	Value
MFI@190°C, 2.16 kg	ISO 1133	gr/10min	0.9 - 1.1
Density	ISO 1183	gr/ml	0.934 - 0.938
Dart Impact	ASTM D1709-03	gr	71
Haze	ASTM D1003-11	--	18.2
Tensile STR.@ Yield	ASTM D882-10	Mpa	17.2
Tensile STR.@ Break	ASTM D882-10	Mpa	
Elong.@ Break	ASTM D882-10	%	938
Gloss(60°C)	ASTM D2457-08	--	79.5
Tear	ASTM D1922-09	N	MD: 0.53 TD: 1.25