



NAME: PGPC 0104

Application:
Suitable for Extrusion.

Typical data: (Table)

PROPERTY	CONDITION	UNIT	TEST METHOD	VALUE
General Property				
Density		g/cm ³	ASTM D-792	1.20
Melt Flow Rate (MFR)	@ 300° C 1.2 kgs load	g/10 mins	ASTM D-1238	
Mechanical Property				
Tensile Strength	@ Yield	Mpa	ASTM D-638	> 60
Tensile Stress	@ Yield	Mpa	ASTM D-638	60-70
Elongation Strain	@ Break	%	ASTM D-638	> 100
Modulus of Elasticity		Mpa	ASTM D-638	2200 -2400
Charpy Impact Strength	Notched	Kj/m ²	ASTM D-256	> 30
Ball Indentation Hardness		N/mm ²	DIN 53456	>103
Electrical Property				
Di-Electric Strength	@ 50 Hz Diameter=50mm Thickness = 2 mm	Kv/mm	ASTM D-149	> 20
Di-Electric Constant	@ 1 MHz		ASTM D-150	2.8-3.1
Loss Index	@ 1 MHz		ASTM D-150	0.008 -0.011
Loss Index	@ 50 MHz		ASTM D-150	0.0008 -0.001
Thermal Property				
Vicat Softening Temperature	50 N, 50 ° C /h	° C	ASTM D-1525	145 -150
Optical Property				
Transmittance	@ Thickness 2 mm	%	ASTM D-1003	> 80
Solvent Content		ppm	GC	500 max

Packaging: 500-1000 kg Big Bag 25 Kg Bags.