



NAME: S 28 F

Product Description:

The grade is for the production of biaxial oriented poly propylene films and is particularly suitable for metallization.

Applications:

- Cosmetics, food stuffs, lamination and other flexible films.

Typical data: (Table)

Property	Unit	Typical Value	Test Method
M.F.I	Dg/min	2	ISO 1133
Density	g/cm ³	0.9	ISO 1183
Flexural Modulus	N/mm ²	1450	ISO 178
Tensile	N/mm ²	35	ISO R527
Elongation	%	13	ISO R527
Izod Impact	Kj/m ²	6.5	ISO 180
Hardness	point	71	ISO 868
Vicat	°C	155	ISO 306/A
H.D.T	°C	105	ISO 75/B

* Typical Values: not to be construed as specifications.

Packing: 25 Kg plastic bag