



### **NAME: SD0150**

#### **Product Description:**

SD0150 is one of the styrenic terpolymer (ABS) grade with improved toughness versus HIPS grades. SD0150 exhibits, low shrinkage, and good dimensional stability. SD0150 is widely used in general injection molding applications. Use this information as a guide to aid you in selecting the proper resin for your application.

#### **Applications:**

Furnitures, Automotive Parts, General Injection Molding, Appliances Casing, Office Supplies.

#### **Drying:**

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content 0.1%. Typical drying conditions are 2 hours at 180° - 190°F (82° - 88°C). Drying for 4 hours at 160° - 170°F (71°-77°C) is also adequate.

#### **Typical data: (Table)**

PROPERTY	UNIT	METHOD	VALUE
MELT FLOW INDEX (200°C/5KG)	GR/10MIN	ASTM D-1238	1.8
IZOD IMPACT STRENGTH	KGF.CM/C	ASTM D-256	22
VICAT SOFTENING POINT(5KGF LOAD)	°C	ASTM D-1525	98
TENSILE STRENGTH AT YEILD	KGF/CM2	ASTM	450
FLEXURAL STRENGTH AT YEILD	KGF/CM2	ASTM D-790	600
FLEXURAL MODULUS	KGF/CM2	ASTM D-790	22000
ROCKWELL HARDNESS(AT 23°C)	R.SCALE	ASTM D-785	105

\*All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information About guaranteed items, please refer to S.S.S. (Standard Sales Specifications)